

VAPOR IN 120

PARNA KOČNICA



SASTAV

- 1 gornji sloj: film parne kočnice od materijala PP
- 2 donji sloj: netkana tkanina od materijala PP



TEHNIČKI PODATCI

Svojstvo	norma	vrijednost	USC units
Gramatura	EN 1849-2	120 g/m ²	0.39 oz/ft ²
Debljine	EN 1849-2	0,4 mm	16 mil
Prijenos vodene pare (Sd) ⁽¹⁾	EN 1931/EN ISO 12572	30 m	0.14 US Perm
Otpornost na vlak MD/CD ⁽¹⁾	EN 12311-2	220/180 N/50 mm	25/21 lbf/in
Istezanje MD/CD ⁽¹⁾	EN 12311-2	47/68 %	–
Otpornost na cijepanje čavla, MD/CD ⁽¹⁾	EN 12310-1	160/205 N	36/46 lbf
Vodonepropusnost	EN 1928	sukladno	–
Otpornost na vodenu paru:			
– nakon umjetnog starenja	EN 1296/EN 1931	sukladno	–
– u prisutnosti alkalija	EN 1847/EN 12311-2	npd	–
Reakcija na požar	EN 13501-1	razred E	–
Otpornost na prolazak zraka	EN 12114	<0,02 m ³ /(m ² h50Pa)	0 cfm/ft ² at 50Pa
Otpornost na temperaturu	–	-20/80 °C	-4/176 °F
Neizravno izlaganje ultraljubičastim (UV) zrakama	–	Dva (2) tjedna	–
Toplinska vodljivost (λ)	–	0,3 W/(m·K)	0.17 BTU/h·ft·°F
Specifična toplota	–	1800 J/(kg·K)	–
Gustoća	–	oko 300 kg/m ³	oko 19 lbm/ft ³
Faktor otpornosti na paru (μ)	–	oko 75000	oko 150 MNs/g
HOS (VOC)	–	nije relevantno	–

⁽¹⁾ Srednje vrijednosti dobivene na osnovi laboratorijskih ispitivanja. Kako biste doznali minimalne vrijednosti, pogledajte izjavu o svojstvima.

🗑️ Razvrstavanje otpada (2014/955/EU): 17 02 03.

KODOVI I DIMENZIJE

KOD	opis	tape	H [m]	L [m]	A [m ²]	H [ft]	L [ft]	A [ft ²]	
VV120	VAPOR IN 120	–	1,5	50	75	5	164	807	36
VV12030	VAPOR IN 120 3,0 m	–	3	50	150	10	164	1615	30